

## DECLARATION OF PERFORMANCE No. P2-FPC-2013-07-15

1. Unique identification code of the product-type:

**Particleboard PB E1 P2**

2. Identification of the construction product:

**Kronospan SRB; PB E1 P2; 1393-CPD-0579**

Identification code is printed on the each board and consists of production plant, product type, production date and time; and/or is printed on the label attached to the production boards packing.

3. Intended use or uses of the construction product:

**For internal use as a non-structural component in dry conditions  
(P2 acc. EN 312 is non load-bearing boards for use in dry conditions)**

4. Name and contact address of the manufacturer:

**KRONOSPAN SRB d.o.o**  
**17. marta 2**  
**34 220 Lapovo**  
**REPUBLIKA SRBIJA**  
[www.kronospansrb.rs](http://www.kronospansrb.rs)  
MB: 20238755 PIB: 104778805

5. System of assessment and verification of constancy of performance:

**System 3**

6. The notified factory production control certification body:

**Timber Research and Development Institute, Prague**  
**(Výzkumný a vývojový ústav dřevařský, Praha,s.p.)**  
**Na Florenci 7-9,**  
**111 71 Praha 1**  
**Czech Republic**  
[www.vvud.cz](http://www.vvud.cz)  
**Notified body no. 1393**

The notified factory production control certification body- **Timber Research and Development Institute, Prague** - performed initial inspection of the manufacturing plant and of factory production control and performs continuous surveillance, assessment and evaluation of factory production control under the system 3 as described in harmonised standard **EN 13986: 2004**

Notified body issued the certificate of conformity of the factory production control

**No. 1393-CPD-0579**

7. Declared performance

Essential characteristics	Performance					Harmonised technical specification
	Boards thickness in mm					
	8 – 13	> 13 – 20	> 20 – 25	> 25 – 32	> 32 – 40	
Bending strength <sup>1</sup> acc. EN 310	11 MPa	11 MPa	10,5 MPa	9,5 MPa	8,5 MPa	EN 13986:2004
Bending stiffness <sup>1</sup> (Modulus of elasticity) acc. EN 310	1800 MPa	1600 MPa	1500 MPa	1350 MPa	1200 MPa	
Tensile strength (Internal bond) acc. EN 319	0,40 MPa	0,35 MPa	0,30 MPa	0,25 MPa	0,20 MPa	
Release of content of formaldehyde acc. EN 120	Class E1 ( ≤ 8 mg/ 100g oven dry board)					
Reaction to fire acc. EN 13501-1	D-s1,d0					
Water vapour permeability	NPD					
Airborne sound insulation	NPD					
Sound absorption	NPD					
Thermal conductivity	NPD					
Strength and stiffness for structural use	NPD					
Mechanical durability	NPD					
Biological durability acc. EN 353	NPD					
Release (Content) of pentachlorophenol (PCP)	NPD					

<sup>1</sup> The table values of strength are not characteristic values for use in the design of wood framed structures (e.g. according to EN 1995-1-1).

8. The performance of the product identified in points 1 and 2 is in conformity with the declared performance in point 7.

This declaration of performance is issued under the sole responsibility of the manufacturer identified in point 4.

Signed for and on behalf of the manufacturer by:

Dragica Milojković, Quality control manager  
 (name and function)



Lapovo, 15.07.2013.  
 (place and date of issue)

(signature)